



PVC: 90-500 µm

Flexaoffice NS 30 is a rigid calandered PVC film with both sides identically glossy. It is notable for the homogeneous brilliance and transparency of both surfaces. Along with the absence of defects, this makes the product suitable for transparent windows, adhesive tapes or stationary applications. It has very high impact and a good heat resistance. This product is available in different sizes, both in sheets and rolls.

Note: To avoid brittleness, we recommend to store the material for at least 48 h at room temperature before using.

Description	Method	Values
PVC Thickness		90 – 500 µm
Thickness tolerance	GALLAZZI MC-07	< 200 µm ± 8% > 200 µm ± 5%
Specific gravity	ASTM D792	1.340 g/cm ³
Apparent specific gravity	GALLAZZI MC-36	1.340 g/cm ³
Tensile strength at break (MD)	ASTM D882	25 – 40 MPa
Elongation at break (MD)	ASTM D882	50 – 120 %
Vicat softening point	ASTM D1525	84 °C ± 1°
Gloss 60° (both sides)	ASTM D2457	> 90 g.u.
Wetting tension (both sides)	ASTM D2578	34 – 36 dyne/cm
Width		max. 165 cm
Width tolerance		± 1 mm
Tensile impact	DIN 53448	> 550 kJ/m ²

All the above data and information represent the current state of our knowledge. It is given in good faith but without any guarantee. It is responsibility of the user to ensure that the product complies with his requirement and with any legislation related to its use.